



BYOCELL RH

BYOCELL RH is a high performance cationic polymer in aqueous solution. Its main function is increasing the wet strength in paper, either in acid or alkaline media, however it is a good aid in drainage and drying of paper. It acts as a cationizing agent.

Properties

<i>Appearance:</i>	Amber liquid
<i>pH :</i>	4.0 – 6.0
<i>Solubility in water:</i>	100% Soluble
<i>Freezing point:</i>	-1.65 °C
<i>Boiling point:</i>	100 °C
<i>Shelf life:</i>	3 months

Applications

BYOCELL RH is highly effective to increase the wet strength of toilet paper, facial tissue, napkins, towels, corrugated, bag paper, paperboard and other specialties.

BYOCELL RH performs over a broad pH range of 4.0 - 9.0, however the best performance is in a pH range of 6.5 - 8.0, previously diluted and added to a high consistency furnish with good stirring. **BYOCELL RH** should be added after rosin size and alum addition. Typical doses are in the range of 0.2% - 1.0% (dry base), which depends directly from the desired wet strength grade.

FDA Regulations

BYOCELL RH can be used as a compound in paper and paperboard manufacturing for packaging in direct contact with fatty and aqueous foods(21 CFR 176.170(a)(5)) and for packaging in direct contact with dry foods(21 CFR 176.180) which are FDA approved. Resin must not exceed 1.5% by weight of the paper or paperboard.

Basicos y Colorantes, S.A. de C.V.

San Francisco No 12, Col. San Francisco Cuautlalpan, Naucalpan Edo. de México
Tel. +52 55 5358-2011, Fax. +52 55 5358-2685, <http://www.byc.com.mx>

Packaging and Storage

BYOCELL RH is not classified as a hazardous product. This product must be stored at temperatures lower than 25°C to extend the shelf life. This product should be stored in acid-resistant, lined steel or glass fiber tanks and containers

Packing: 1,000 Kg. containers.

The information above is believed to be accurate and represents the best information currently available to us. However, we make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and we assume no liability resulting from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. Básicos y Colorantes S.A. de C.V. will not be responsible for damages resulting from use of or reliance upon this information.

Basicos y Colorantes, S.A. de C.V.

San Francisco No 12, Col. San Francisco Cuautlalpan, Naucalpan Edo. de México
Tel. +52 55 5358-2011, Fax. +52 55 5358-2685, <http://www.byc.com.mx>