

## PAPERSOFT

**Papersoft** is a liquid cationic softener water-soluble, for the tissue paper production. This product also acts as an excellent de-bonding agent.

### Advantages

- Give excellent softness to fibers.
- Product in liquid form, water-soluble.
- Wet strength and dry strength effective.
- Non-ionic and cationic auxiliaries compatible.

### Properties

<i>Appearance:</i>	Creamy beige liquid
<i>Chemical nature:</i>	Fatty Amino amide derivative
<i>Ionic Character:</i>	Cationic
<i>pH (1%):</i>	3.5 – 4.5
<i>Shelf life:</i>	12 months

### Applications

**Papersoft** is recommended to use a dosage of 0.3 – 10.0 Kg/ton, it can be added directly from container, but its effectiveness is better if it is made a previous dilution of 1%-5% before to be added to system. The application points can be in furnish just before the sheet formation or in the Yankee sprayer. **Papersoft** is compatible with the most of additives for wet strength.

### Packaging and Storage

**Papersoft** is recommended to be stored in polyethylene, polypropylene or stainless steel containers. The product may solidify at temperatures lower than 15°C, because of that is recommended store it between 20°C and 35°C. The references to the firefighting and accident measures, as well as the information about environment are contained in the material safety data sheet.

La información contenida en esta hoja, así como cualquier sugerencia técnica – sea en forma verbal, escrita o por ensayos – se basa en nuestros conocimientos actuales, y son dados de buena fe sin garantía alguna. Por lo que nuestras sugerencias no lo liberan de la obligación de comprobar su validez de acuerdo a sus necesidades, a su producción, a sus condiciones y propósitos. La aplicación, uso y proceso de nuestros productos y los productos manufacturados por usted y la base de nuestras sugerencias técnicas están fuera de nuestro control por lo que son su responsabilidad.

**Básicos y Colorantes, S.A. de C.V.**

San Francisco No 12, Col. San Francisco Cuautlalpan, Naucalpan Edo. de México  
Tel. +52 55 5358-2011, Fax. +52 55 5358-2685, <http://www.byc.com.mx>